



Designation: D 4143 – 89 (Reapproved 1996)^{€1}

AMERICAN SOCIETY FOR TESTING AND MATERIALS
100 Barr Harbor Dr., West Conshohocken, PA 19428
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Guide for Testing Latex Vehicles¹

This standard is issued under the fixed designation D 4143; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{€1} NOTE—Keywords were added editorially in October 1996.

1. Scope

1.1 This guide covers methods suitable for testing latex vehicles. Certain of these methods were developed expressly for testing latex vehicles. Others were developed for testing or analyzing formulated water- or solvent-based coatings but would be equally applicable for testing lattices.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- D 562 Test Method for Consistency of Paints Using the Stormer Viscometer²
- D 1417 Test Methods for Rubber Latices—Synthetic³
- D 1475 Test Method for Density of Paint, Varnish, Lacquer, and Related Products²
- D 2196 Test Methods for Rheological Properties of Non-Newtonian Materials by Rotational (Brookfield) Viscometer²
- D 2354 Test Method for Minimum Film Formation Temperature (MFT) of Emulsion Vehicles⁴
- D 2369 Test Method for Volatile Content of Coatings²
- D 3168 Practice for Qualitative Identification of Polymers in Emulsion Paints²
- D 3792 Test Method for Water Content of Water-Reducible Paints by Direct Injection Into a Gas Chromatograph²
- D 3925 Practice for Sampling Liquid Paints and Related Pigmented Coatings²
- D 4017 Test Method for Water in Paints and Paint Materials by Karl Fischer Method²
- D 4758 Test Method for Nonvolatile Content of Latexes⁴

¹ This guide is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.33 on Polymers and Resins.

Current edition approved March 31, 1989. Published May 1989. Originally issued as D4143 – 82. Last previous edition D 4143 – 82.

² Annual Book of ASTM Standards, Vol 06.01.

³ Annual Book of ASTM Standards, Vol 09.01.

⁴ Annual Book of ASTM Standards, Vol 06.03.

TABLE 1 Methods for Testing Latex Vehicles

Test Method	Section	ASTM Designation
Latex sampling methods	3	D 3925
Nonvolatile content	3.1	D 2369; D 4758
Minimum film formation temperature (MFT)	5	D 2354
Qualitative polymeric analysis	6	D 3168
Density	7	D 1475
Viscosity	8	D 2196
Consistency	9	D 562
Water content	10	D 3792; D4017
pH	11	E 70
Surface tension	12	D 1417

E 70 Test Method for pH of Aqueous Solutions with the Glass Electrode⁵

3. Latex Sampling Methods

3.1 Practice D 3925 describes sampling procedures for formulated (pigmented) coatings that are equally applicable to latex vehicles.

4. Nonvolatile Content

4.1 Test Method D 2369 has been found suitable for the determination of the volatile content of many latex vehicles. Nonvolatile content is obtained by subtracting the results from 100.

NOTE 1—Determinations of the volatile content using a shorter bake time than the 60 min recommended in Test Method D 2369 should be noted in the report of the results.

4.2 The nonvolatile content of latexes may also be determined for quality control purposes with Test Method D 4758 which specifies baking at 180°C for 20 min, conditions selected to allow completion of testing in 1 h or less. For latex vehicles used in certain air-dry or low temperature bake coatings, as well as for those that contain temperature-sensitive materials, the use of the milder test conditions of Test Method D 2369 (see 4.1) will more accurately reflect the effective nonvolatile content.

4.2.1 Test Method D 4758 is not intended to be employed for determining the volatile organic content (VOC) of formulated coatings.

⁵ Annual Book of ASTM Standards, Vol 15.05.

5. Minimum Film Formation Temperature (MFT)

5.1 The MFT is the lowest temperature at which a latex will form a continuous film. Test Method D 2354 employs draw-down application of the test latex on a substrate over which a temperature gradient has been established. The lowest temperature at which the latex is converted into a clear, continuous film corresponds to the minimum film formation temperature.

6. Qualitative Polymer Analysis

6.1 Chemical identification of the polymeric material contained in a latex is readily determined by a method that was developed for polymer analysis of formulated latex paints. Practice D 3168 employs a sequence of drying and subsequent extraction and solution procedures that remove volatile and nonvolatile nonpolymeric materials and isolate the polymeric solids of the latex. The major components of the isolated polymeric material are qualitatively identified by infrared absorption or pyrolysis-gas chromatographic techniques, or both.

7. Density

7.1 The density of a latex is its weight (mass) per unit volume and is usually expressed as weight per gallon or grams per millilitre at a specified temperature. At constant latex nonvolatile content, the density of various latex materials can vary depending on the density of the contained polymer solids. Test Method D 1475 is a general method for determining the density of fluid formulated coatings and components thereof and is therefore equally applicable for determination of the density of lattices.

8. Viscosity

8.1 Lattices are non-Newtonian materials having rheological properties that can be characterized by apparent viscosity measurements made using rotational-type viscometers. Test

Methods D 2196 describes techniques using a Brookfield viscometer by which apparent viscosity can be measured and relative shear rate and time dependence of apparent viscosity can be assessed.

9. Consistency

9.1 Consistency of formulated fluid paints, lacquers, varnishes, and their individual fluid components, including high-viscosity lattices, are frequently measured using the Stormer viscometer. Test Method D 562 describes operation of the Stormer viscometer for measuring the consistency of such materials either with or without a stroboscopic timer.

10. Water Content

10.1 Although the major component of the volatile material in a latex is usually water, other volatile components may be present. Test Method D 3792 was developed for determining the water content of liquid latex coatings by direct injection into a gas chromatograph. This method is equally suitable for determining water content of lattices. Test Method D 4017 is based on the Karl Fischer method and is also applicable for determining the water content of lattices.

11. pH

11.1 The pH of a latex can be measured by the general procedure described for aqueous solutions in Test Method E 70.

12. Surface Tension

12.1 The surface tension of latex may be determined by the technique given in Test Method D 1417. It is useful as a quality control/assurance test, and as an indicator of the wetting characteristics.

13. Keywords

13.1 latex vehicles; lattices

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.