



Designation: D 3724 – 82 (Reapproved 1995)^{ε1}

AMERICAN SOCIETY FOR TESTING AND MATERIALS
100 Barr Harbor Dr., West Conshohocken, PA 19428
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Specification for Synthetic Brown Iron Oxide Pigment¹

This standard is issued under the fixed designation D 3724; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Keywords were added editorially in May 1995.

1. Scope

1.1 This specification covers the pigments commercially known as synthetic pure brown iron oxides and blends. These pigments are suitable for use in paints and coatings. Methods of manufacture are:

1.1.1 Precipitation of iron salts.

1.1.2 Calcination of precipitated iron oxides.

1.1.3 Blends of synthetic red, yellow, and black iron oxides.

1.1.4 Blends of synthetic red, yellow, and black iron oxides plus the addition of carbon black to a maximum of 5.0 %. Small amounts of carbon black are added to obtain tinting colors not obtainable when synthetic brown iron oxide or carbon black are used singly.

2. Referenced Documents

2.1 ASTM Standards:

D 50 Test Methods for Chemical Analysis of Yellow, Orange, Red, and Brown Pigments Containing Iron and Manganese²

D 185 Test Methods for Coarse Particles in Pigments, Pastes, and Paints²

D 280 Test Methods for Hygroscopic Moisture (and Other Matter Volatile Under the Test Conditions) in Pigments²

D 387 Test Method for Color and Strength of Color Pigments with a Mechanical Muller³

D 1208 Test Methods for Common Properties of Certain Pigments²

D 3872 Test Method for Ferrous Iron in Iron Oxides²

E 350 Test Methods for Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron⁴

E 351 Test Methods for Chemical Analysis of Cast Iron—All Types⁴

3. Composition and Properties

3.1 The pigment shall be a manufactured iron oxide or a

blend. It shall be a soft dry finely pulverized pigment and shall conform to the following requirements:

FeO	0 to 10 %
Fe ₂ O ₃	83 to 98 %
Carbon black, max, %	5.0 %
Moisture and other volatile matter, max, %	1.0 %
Organic coloring matter	none
Total sulfates expressed as SO ₃ , max, %	2.0 %
Coarse particles (total residue retained on No. 325 (45-μm) mesh sieve, max, %	1.0 %
Matter soluble in water, max, %	0.5 %

3.2 Inasmuch as synthetic brown iron oxides are available in a wide range of shades. The mass color and character of the tint and the tinting strength formed by a mixture with a white pigment shall be within mutually agreed upon limits of a standard acceptable to both the purchaser and the seller when tested by Test Method D 387.

4. Sampling

4.1 Two samples shall be taken at random from different packages from each lot, batch, day's pack, or other unit of production in a shipment. When no markings distinguishing between units of production appear, samples shall be taken from different packages in the ratio of two samples for each 5 tons (inch-pound or SI), except that for shipments of less than 10 000 lb two samples shall be taken. At the option of the purchaser, the samples may be tested separately or after blending in equal quantities the samples from the same production unit to form a composite sample.

5. Test Methods

5.1 Tests shall be conducted in accordance with the appropriate ASTM test methods. Test procedures not covered by ASTM test methods shall be mutually agreed upon between the purchaser and the seller.

5.1.1 *Total Iron Oxide, Sulfur and Organic Coloring Matter*—Test Methods D 50.

5.1.2 *Ferrous Iron Content*—Test Method D 3872.

5.1.3 *Moisture and Other Volatile Matter*—Test Method D 280—Use Method A for pigments containing less than 8 % ferrous iron oxide. Use Method B for pigments containing more than 8 % ferrous iron oxide.

5.1.4 *Matter Soluble in Water*—Test Method D 1208.

5.1.5 *Coarse Particles in Dry Pigment*—Test Method D 185.

¹ This specification is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.31 on Pigment Specifications.

Current edition approved Oct. 29, 1982. Published January 1983. Originally published as D 3724 – 78. Last previous edition D 3724 – 78.

² *Annual Book of ASTM Standards*, Vol 06.03.

³ *Annual Book of ASTM Standards*, Vol 06.01.

⁴ *Annual Book of ASTM Standards*, Vol 03.05.

5.1.6 Carbon Black Content—Test Methods E 350 or
E 351.

6. Keywords

6.1 brown iron oxide; pigment; synthetic

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.