



## Standard Test Method for Volatile Content of Coatings<sup>1</sup>

This standard is issued under the fixed designation D 2369; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This test method describes a procedure for the determination of the weight percent volatile content of solventborne and waterborne coatings. Test specimens are heated at  $110 \pm 5^\circ\text{C}$  for 60 min.

NOTE 1—The coatings used in these round-robin studies represented air-dried, air-dried oxidizing, heat-cured baking systems, and also included multicomponent paint systems.

1.2 Sixty minutes at  $110 \pm 5^\circ\text{C}$  is a general purpose test method based on the precision obtained with both solventborne and waterborne coatings (see Section 9). These coatings (single package, heat cured) are commonly applied in factories to automobiles, metal containers, flat (coil) metal and large appliances, and many other metal parts.

1.3 This test method is viable for coatings wherein one or more parts may, at ambient conditions, contain liquid coreactants that are volatile until a chemical reaction has occurred with another component of the multi-package system.

NOTE 2—Committee D-1 has run round-robin studies on volatiles of multicomponent paint systems. The only change in procedure is to premix the weighed components in the correct proportions and allow the specimens to stand at room temperature for 1 h prior to placing them into the oven.

1.4 This test method may not be applicable to all types of coatings. Other procedures may be substituted with mutual agreement between the producer and the user.

NOTE 3—If unusual decomposition or degradation of the specimen occurs during heating, the actual time and temperature used to cure the coating in practice may be substituted for the time and temperature specified in this test method, subject to mutual agreement between the producer and the user. The U.S. EPA Reference Method 24 specifies  $110 \pm 5^\circ\text{C}$  for 1 h for coatings.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For a specific

hazard statement see Note 12.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

D 362 Specification for Industrial Grade Toluene<sup>2</sup>

D 1193 Specification for Reagent Water<sup>3</sup>

D 3925 Practice for Sampling Liquid Paints and Related Pigmented Coatings<sup>4</sup>

E 145 Specification for Gravity-Convection and Forced-Ventilation Ovens<sup>5</sup>

E 180 Practice for Determining the Precision Data of ASTM Methods for Analysis and Testing of Industrial Chemicals<sup>6</sup>

#### 2.2 Other Standards:

EPA Reference Method 24—Determination of Volatile Matter Content, Density, Volume Solids, and Weight Solids of Surface Coatings<sup>7</sup>

### 3. Summary of Test Method

3.1 A designated quantity of coating specimen is weighed into an aluminum foil dish containing 3 mL of an appropriate solvent, dispersed, and heated in an oven at  $110 \pm 5^\circ\text{C}$  for 60 min. The percent volatile is calculated from the loss in weight.

### 4. Significance and Use

4.1 This test method is the procedure of choice for determining volatiles in coatings for the purpose of calculating the volatile organic content in coatings under specified test conditions. The weight percent solids content (nonvolatile matter) may be determined by difference. This information is useful to the paint producer and user and to environmental interests for determining the volatiles emitted by coatings.

### 5. Apparatus

5.1 *Analytical Balance*, capable of weighing  $\pm 0.0001$  g.

5.2 *Aluminum Foil Dishes*, 58 mm in diameter by 18 mm high with a smooth (planar) bottom surface. Precondition the

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.21 on Chemical Analysis of Paints and Paint Materials.

Current edition approved Nov. 10, 1998. Published January 1999. Originally published as D 2369 – 65 T. Last previous edition D 2369 – 97.

<sup>2</sup> Discontinued; see 1991 Annual Book of ASTM Standards, Vol 06.03.

<sup>3</sup> Annual Book of ASTM Standards, Vol 11.01.

<sup>4</sup> Annual Book of ASTM Standards, Vol 06.01.

<sup>5</sup> Annual Book of ASTM Standards, Vol 14.02.

<sup>6</sup> Annual Book of ASTM Standards, Vol 15.05.

<sup>7</sup> Available from Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

dishes for 30 min in an oven at  $110 \pm 5^\circ\text{C}$  and store in a desiccator prior to use. Use tongs or rubber gloves, or both, to handle the dishes.

5.3 *Forced Draft Oven*, Type IIA or Type IIB as specified in Specification E 145.

NOTE 4—Be sure the shelves are level.

5.4 *Syringe*, 1-mL, capable of properly dispensing the coating under test at a sufficient rate so that the specimen can be dissolved in the solvent.

NOTE 5—Disposable syringes are recommended.

5.5 *Paper Clips*.

## 6. Reagents

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.<sup>8</sup> Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

6.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean Type II of Specification D 1193.

6.3 *Toluene*, technical grade, Specification D 362.

## 7. Procedure

7.1 Take a representative sample of the liquid coatings in accordance with Practice D 3925. Mix thoroughly before taking specimens for individual tests. If air bubbles become entrapped, stir by hand, until the air has been removed.

NOTE 6—For waterborne paint systems it is recommended that they be stirred by hand.

7.2 Using a syringe weigh to 0.1 g, by difference, the correct specimen weight according to the following:

Expected % Nonvolatile	Expected % Volatile	Specimen Weight, g
60 % or more	40 % or less	$0.3 \pm 0.1$
Less than 60 %	more than 40 %	$0.5 \pm 0.1$

The specimen is added to a tared aluminum foil dish ( $W_1$ ) into which has been added  $3 \pm 1$  mL of suitable solvent (6.2 or 6.3). Add the specimen dropwise, shaking (swirling) the dish to disperse the specimen completely in the solvent. If the material forms a lump that cannot be dispersed, discard the specimen and prepare a new one.

NOTE 7—To facilitate dispersing the sample completely in the solvent, a metal paper clip may be placed (partially unfolded to use as a stirrer) in the preconditioned aluminum dish before weighing. The clip may then be used as a stirrer to completely disperse the specimen into the solvent. Be sure to leave the paper clip in the dish throughout the remainder of the procedure (through 7.5).

<sup>8</sup> *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

7.2.1 Similarly prepare a duplicate.

7.2.2 The result obtained is based on the mean of the results obtained in 7.2 and 7.2.1.

NOTE 8—Be sure to wipe the outer surface of the syringe clean after obtaining the specimen. Pull the syringe plunger up  $\frac{1}{4}$  in. (6.4 mm) in order to pull the specimen away from the neck of the syringe. Cap and weigh. After dispensing the paint specimen do not wipe the tip of the syringe. Remove the specimen from the neck of the syringe by pulling up the plunger. Cap and reweigh.

NOTE 9—Use disposable (no talc) rubber gloves or polyethylene to handle the syringe.

NOTE 10—If the specimen cannot be dispersed in the solvents listed (6.2 or 6.3), a compatible solvent may be substituted provided it is no less volatile than 2-ethoxyethyl acetate.

7.3 For multicomponent systems, weigh the components in the proper proportion into containers that can be capped. Mix the components together immediately, weigh the appropriate sample size from the table in 7.2, as specified into the aluminum weighing dishes containing  $3 \pm 1$  mL of a suitable solvent. After dispersing, allow to stand for 1 h at room temperature (induction period) before placing the dishes into the oven.

NOTE 11—Other induction periods are used. See U.S. EPA Reference Method 24.

7.4 Heat the aluminum foil dishes containing the dispersed specimens in the forced draft oven (5.3) for 60 min at  $110 \pm 5^\circ\text{C}$ .

NOTE 12—**Precaution:** In addition to other precautions, provide adequate ventilation, consistent with accepted laboratory practice, to prevent solvent vapors from accumulating to a dangerous level.

7.5 Remove the dishes from the oven, place immediately in a desiccator, cool to ambient temperature, and weigh to 0.1 mg.

## 8. Calculation

8.1 Calculate the percent volatile matter,  $V$ , in the liquid coating as follows:

$$V_A = 100 - [(W_2 - W_1)/S_A] \times 100 \quad (1)$$

where:

$V_A$  = % volatiles (first determination),

$W_1$  = weight of dish,

$W_2$  = weight of dish plus specimen after heating,

$S_A$  = specimen weight, and

$V_B$  = % volatiles (duplicate determination, calculate in same manner as  $V_A$ ).

$$V = (V_A + V_B)/2 \quad (2)$$

8.2 Report  $V$ , the mean of the duplicate determination if relative percent difference is 1.5 % or less. If relative difference between  $V_A$  and  $V_B$  is greater than 1.5 %, repeat the duplicate determinations.

8.3 The percent of nonvolatile matter,  $N$ , in the coating may be calculated by difference as follows:

$$N = (N_A + N_B)/2 \quad (3)$$

where:

$N_A = 100 - V_A$ , and

$N_B = 100 - V_B$ .

$N_A$  represents first determination and  $N_B$  represents duplicate determination.

## 9. Precision and Bias

9.1 The precision estimated for tests at 60 min at  $110 \pm 5^\circ\text{C}$  are based on an interlaboratory study<sup>9</sup> in which 1 operator in each of 15 laboratories analyzed in duplicate on 2 different days 7 samples of waterborne paints and 8 samples of solventborne paints containing between 35 and 72 % volatile material. The paints were commercially supplied. The results were analyzed statistically in accordance with Practice E 180. The within-laboratory coefficient of variation was found to be 0.5 % relative at 213 df and the between-laboratories coefficient of variation was 1.7 % relative at 198 df. Based on these coefficients, the following criteria should be used for judging the acceptability of results at the 95 % confidence level.

9.1.1 *Repeatability*—Two results, each the mean of duplicate determinations, obtained by the same operator on different days should be considered suspect if they differ by more than 1.5 % relative.

9.1.2 *Reproducibility*—Two results, each the mean of duplicate determinations, obtained by operators in different laboratories should be considered suspect if they differ by more than 4.7 % relative.

9.2 *Bias*—Bias has not been determined.

9.3 The precision results for multicomponent systems are based on an interlaboratory study in which one operator in each of five laboratories analyzed in duplicate on two different days, four samples of commercially supplied solventborne and waterborne multicomponent systems. The results were analyzed statistically in accordance with Practice E 180.

9.3.1 *Repeatability for Solventborne Multicomponent Systems*:

Coefficient of variation	0.5 %
Degrees of freedom	6
Factor (based on 95 % confidence level)	3.46
Precision	1.74 %

Two results, each the mean of duplicate determinations obtained by the same operator on different days, should be considered suspect if they vary by more than 1.74 % relative.

9.3.2 *Reproducibility for Solventborne Multicomponent Systems*:

Coefficient of variation	1.46 %
Degrees of freedom	5
Factor (based on 95 % confidence level)	3.46
Precision	5.31 %

Two results, each the mean of duplicate determinations obtained by operators in different laboratories, should be considered suspect if they vary by more than 5.31 % relative.

9.3.3 *Repeatability for Waterborne Multicomponent Systems*:

Coefficient of variation	0.53 %
Degrees of freedom	6
Factor (based on 95 % confidence level)	3.46
Precision	1.84 %

Two results, each the mean of duplicate determinations obtained by the same operator on different days, should be considered suspect if they vary by more than 1.84 % relative.

9.3.4 *Reproducibility for Waterborne Multicomponent Systems*:

Coefficient of variation	0.94 %
Degrees of freedom	5
Factor (based on 95 % confidence level)	3.64
Precision	3.43 %

Two results, each the mean of duplicate determinations obtained by operators in different laboratories, should be considered suspect if they vary by more than 3.43 % relative.

## 10. Keywords

10.1 multicomponent paints; nonvolatile determination; VOC baking temperature; VOC in paints; volatile determination; volatiles

<sup>9</sup> Supporting data are available from ASTM Headquarters. Request RR: D01-1026.

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*