



Standard Practice for Determining the Effect of Overbaking on Organic Coatings¹

This standard is issued under the fixed designation D 2454; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers the determination of the time-temperature effect of overbaking on the physical and chemical properties of organic coatings.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of whoever uses this standard to consult and establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific hazard statements are given in Section 7.

2. Referenced Documents

2.1 ASTM Standards:

- D 522 Test Method for Mandrel Bend Test of Attached Organic Coatings²
- D 523 Test Method for Specular Gloss²
- D 609 Practice for Preparation of Cold-Rolled Steel Panels for Testing Paint, Varnish, Conversion Coatings, and Related Coating Products²
- D 823 Practices for Producing Films of Uniform Thickness of Paint, Varnish, and Related Products on Test Panels²
- D 1005 Test Methods for Measurement of Dry-Film Thickness of Organic Coatings Using Micrometers²
- D 1186 Test Methods for Nondestructive Measurement of Dry Film Thickness of Nonmagnetic Coatings Applied to a Ferrous Base²
- D 1308 Test Method for Effect of Household Chemicals on Clear and Pigmented Organic Finishes³
- D 1400 Test Method for Nondestructive Measurement of Dry Film Thickness of Nonconductive Coatings Applied to a Nonferrous Metal Base²
- D 1640 Test Methods for Drying, Curing, or Film Formation of Organic Coatings at Room Temperature²
- D 1729 Practice for Visual Evaluation of Color Differences of Opaque Materials²
- D 1730 Practices for Preparation of Aluminum and Aluminum-Alloy Surfaces for Painting⁴

- D 1731 Practices for Preparation of Hot-Dip Aluminum Surfaces for Painting⁴
- D 2092 Guide for Preparation of Zinc-Coated (Galvanized) Steel Surfaces for Painting³
- D 2197 Test Method for Adhesion of Organic Coatings by Scrape Adhesion²
- D 2201 Practice for Preparation of Zinc-Coated and Zinc-Alloy-Coated Steel Panels for Testing Paint, and Related Coating Products²
- D 2244 Test Method for Calculation of Color Differences From Instrumentally Measured Color Coordinates²
- D 2794 Test Method for Resistance of Organic Coatings to the Effects of Rapid Deformation (Impact)²
- D 3359 Test Methods for Measuring Adhesion by Tape Test²
- D 3363 Test Method for Film Hardness by Pencil Test²
- E 805 Practice for Identification of Instrumental Methods of Color or Color-Difference, Measurement of Materials²

3. Terminology

3.1 Definition:

3.1.1 *overbaking*—an exposure of the coating to a moderately higher temperature or to a longer period of baking, or both, than recommended by the manufacturer of the coating for normal curing. This condition is in contrast to “heat resistance” which is a parameter relating to the service life of a coating.

4. Summary of Practice

4.1 Four panels are prepared and baked at the schedule normally recommended for the coating. Two of the panels are then removed and the remaining two are subjected to an additional overbake in which the time and temperature are mutually agreed upon between the purchaser and the seller. The sets of panels, after a suitable conditioning interval, are then evaluated for the properties that are compatible with the substrate. Among these are gloss, color, flexibility, adhesion, impact resistance, and resistance to reagents. Note that glass substrates should not be tested for impact, and zinc-coated substrates can influence both flexibility and impact.

5. Significance and Use

5.1 Most coatings are designed for a specific baking time and temperature. For a variety of reasons (line stoppages, rerouting back through ovens, oven overheating, etc.) the prescribed time or temperature, or both, of the bake is often

¹ This practice is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.27 on Accelerated Testing.

Current edition approved Nov. 10, 1995. Published January 1996. Originally published as D 2454 – 66 T. Last previous edition D 2454 – 91.

² *Annual Book of ASTM Standards*, Vol 06.01.

³ *Annual Book of ASTM Standards*, Vol 06.02.

⁴ *Annual Book of ASTM Standards*, Vol 02.05.

exceeded. This practice has been found to be useful in evaluating the effects of overbakes on coatings.

6. Materials

6.1 *Standard Baking-Type Coating* mutually agreed upon between the purchaser and the seller.

7. Hazards

7.1 The flash points of most solvents used in many organic coatings and related products are low enough that adequate ventilation is needed to avoid exceeding 25 % of the lower explosive limits of the solvents when test panels are being prepared and baked. As these materials are considered toxic, take care to avoid inhalation of solvent vapor and unnecessary contact of solvent with the skin.

8. Procedure

8.1 *Application of Organic Coating:*

8.1.1 Apply coatings to steel panels prepared in accordance with Practice D 609.

8.1.2 Apply coatings to zinc-coated surfaces prepared in accordance with Guide D 2092, when zinc has been applied by the hot-dip method or by electroplating.

8.1.3 Apply coatings to nonpassivated galvanized steel prepared in accordance with Practice D 2201, when the zinc is applied by a continuous galvanizing method using an aluminum-bearing zinc.

8.1.4 Apply coatings to aluminum surfaces on all-aluminum materials prepared in accordance with Practices D 1730.

8.1.5 Apply coatings to hot-dip aluminum coated surfaces prepared in accordance with Practices D 1731.

8.1.6 In cases where a primer is used in practice under the topcoat, apply the entire system to the panels. The film thickness of each coat shall be mutually agreed upon between the purchaser and seller, but, in the absence of such agreement, the total thickness shall be 2 ± 0.2 mils (50 ± 5 μm).

8.1.7 In instances where clear coatings are to be tested, they may be applied to aluminum or white carrara glass, one side of which has been polished to a smooth, high-gloss finish. Other selected substrata previously agreed upon between the purchaser and the seller may also be used. In the absence of a specific agreement between the purchaser and the seller in regard to film thickness, apply the coatings by automatic spray. (Refer to Practices D 823, Method A) at a dry film thickness of 2 ± 0.2 mils (50 ± 5 μm). Multiple coats may be used to obtain this film thickness where necessary due to the nature of the coating material (Note 1). Manual spray application or the drawdown method with wire-wound draw bars may be used when automatic equipment is not available.

NOTE 1—Dry film thickness should be measured in accordance with Test Methods D 1005, D 1186, or D 1400, whichever is applicable. The adhesion, flexibility, and color can vary considerably with thickness.

8.2 *Baking:*

8.2.1 The baking schedule for each coating including primer, topcoat, and primer/topcoat systems shall be mutually agreed upon between the purchaser and the seller and shall include the following:

8.2.1.1 *Normal Baking Schedule (Time and Temperature)*

recommended for the development of optimum film properties, and

8.2.1.2 *Overbaking Cycle*—This cycle shall be within practical limits in order to simulate conditions that might be encountered in actual production where baking oven or conveyor lines, or both might malfunction temporarily due to mechanical or electrical failure.

8.3 Prepare four panels of each coating or coating system and bake them at the schedule normally recommended to obtain optimum properties. Conduct the baking of these panels in a mechanical recirculating air oven set to $\pm 2^\circ\text{F}$ ($\pm 1^\circ\text{C}$) of the specified baking temperature. At the end of the specified time remove two panels from the oven and subject the remaining two to the overbake cycle by:

8.3.1 A continuation of the normal bake but for a previously agreed upon time, for example, 50 or 100 % increase in time, or

8.3.2 Resetting the oven temperature to the agreed overbake temperature and then continuing the bake for a specified period of time after the overbake temperature has been reached, or removing the panels until the overbake temperature is reached and then baking them for the agreed upon time.

NOTE 2—The conditions described in 8.3.2 are not usually reproducible between laboratories or different ovens because of variations in the heating characteristics of ovens.

8.3.3 After the sets of panels have been baked according to the mutually agreed upon baking cycles, place them in a suitable rack and condition for 24 h at $73.5 \pm 3.5^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$) and 50 ± 5 % relative humidity (see Test Methods D 1640) prior to testing. Other conditioning terms may be agreed upon between the purchaser and the seller.

9. Test Methods

9.1 Determine the properties of both sets of panels in accordance with any or all of the following ASTM methods:

9.1.1 *Gloss*—Test Method D 523.

9.1.2 *Color*—Practice D 1729 (Visual), Practice E 805 (instrumental), or Test Method D 2244.

9.1.3 *Flexibility*—Test Method D 522 (conical mandrel and cylindrical mandrel).

9.1.3.1 Heat-aged flexibility values should be determined in accordance with a baking cycle that is in agreement between the purchaser and the seller.

9.1.4 *Adhesion*—Test Methods D 2197⁵ (mechanical) or D 3359 (tape), or both.

9.1.5 *Impact Resistance*—Test Method D 2794.⁶

9.1.6 *Hardness*—Test Method D 3363 (pencil test).

9.1.7 *Exposure to Reagents*—If this test is desired, the choice of materials to which the coating is to be exposed shall be governed by the ultimate use of the coating and shall be agreed upon between the purchaser and the seller. The general procedure to be followed in this test is given in Test Method D 1308.

9.1.8 Other tests agreed upon between the purchaser and the seller.

⁵ This test method has been found to be inapplicable for powder coatings.

⁶ It is suggested that impact resistance be determined by use of the Gardner Variable Impact Tester obtainable from the Gardner Laboratory, Inc., Bethesda, MD.

10. Report

10.1 Report the following information:

10.1.1 Substrate employed, including type and thickness,

10.1.2 Type of coating,

10.1.3 Film thickness, including primer, if any,

10.1.4 Normal bake schedule, or schedules,

10.1.5 Overbake cycle,

10.1.6 Test methods employed, and

10.1.7 Values determined, including the measured changes between the normal and overbake cycles.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.